12-142

Special Pathogens Laboratory SPL The Legionella Experts - Pittsburgh, P.

Computer Keyboard Covers Impregnated with a Novel Antimicrobial Polymer Significantly Reduce Microbial Contamination

Natalie D'Antonio, M.S., John D. Rihs, B.S., Melissa Tosiano, B.S., Janet E. Stout, Ph. D.^{1,2} ¹ Special Pathogens Laboratory, Pittsburgh, PA ² University of Pittsburgh, Pittsburgh, PA

Objective

Materials and Methods

0.5 McFarland suspensions (approx. 1.5E+08 cfu/mL) of each organism (MRSA, ATCC No. 43300; VREF, ATCC No. 51299; E. coli,

ATCC No. 25922; and P. aeruginosa, ATCC No. 27853) were prepared

in 1:40 Ringer's solution. The concentration was verified by performing

Polyurethane material squares with and without Biosafe HM 4100

organism suspensions. A 22 mm x 22 mm cover-slip was placed on top

of each inoculated material surface. The recovery of viable bacteria occurred immediately following inoculation (T= 0 min.), sixty minutes

Recovery consisted of placing each cover-slip/material pair into a

tube containing 5 mL of 1:40 Ringer's solution and manually separating the cover-slip from the material. The recovery tube was then vortexed

on high for 30 seconds, dilutions plated on blood agar plates (Remel),

Results

All four organisms exhibited a reduction in viability over the 240

minute time period. Figures 1 through 4

organisms MRSA, VREF, E. coli, and P.

aeruginosa, respectively, on the Biosafe

HM 4100 material versus the control

material at the recovery times

illustrate the log recovery of the test

and colonies enumerated after an overnight incubation at 35°C

after inoculation (T= 60 min.), 120 minutes and 240 minutes after

inoculation (T= 120 min. and T= 240 min., respectively).

were provided by the manufacturer (Biosafe, Inc. Pittsburgh, PA) and

separately inoculated with 40 µL of each of the 1.5E+07 cfu/mL

a viable count assay. The suspension was then diluted 1:10 to yield

approximately 1.5E+07 cfu/mL inoculums.

tix

(plastic) keyboard covers can provide an antimicrobial surface that

minimizes bacterial survival

Abstract

Contact with contaminated computer keyboards may contribute to the transmission of healthcare-acquired infections. A novel antimicrobial polymer (Biosafe HM 4100) can be incorporated infections. A novel antimicrobial polymer (Biosafe HM 4100) can be incorporated into a variety of materials, including the polymerthane (PU) used to make keyboard covers: The study objective was to determine whether plastic keyboard covers compounded with HM 4100 effectively minimize the survival of bacterial species commonly present on environmental surfaces in the healthcare

setting: Polyurethane material with and without HM 4100 was obtained from the manufacturer (Biosafe, Inc. Pittsburgh, PA). Suspensions of approximately 15E+07 cluthu. of four test organisms was prepared and 40 µL of the organism suspension was placed onto the material. Test organisms included Staphylococcus aureus, methicillin resistant (IMR5A). ATCC No. 43200. *Enterococcus facealis* yancomyrch-resistant (INR5F), ATCC No. 51299; E. coli, ATCC No. 25922; P. aeruginosa, ATCC No. 27853. A cover-slip was placed on top of the inoculated material and viable bacteria were recovered after 0, 60, 120, and 240 minutes. The cover-slip and test material were placed in Ringer's solution and vortexed, and dilutions were plated on blood agar and enumerated.


All four test organisms showed a reduction in viability over the 240 minute time period. Percent reduction in viability at T=240 min. on the test material compared to the PU control for MRSA, VREF, *E. coli* and *P. aeruginosa* was 97.8%, 69%, 699.999%,


the FU Gamus newsy, YEE, Level and Severgence and S

incorporation of HM 4100 into computer keyboard covers could reduce the transmission of infections due to hand carriage by healthcare workers during contact with contaminated computer keyboards.

Background

Contaminated computer keyboards have been acknowledged as a potential source for bacterial transmission between healthcare providers and patients, contributing to the high rate of healthcare-associated infections. Biosafe HM 4100 is an antimicrobial polymer that can be incorporated into the polyurethane material used to make keyboard covers. Consequently, a keyboard cover compounded with Biosafe HM 4100 has the potential to minimize disease transmission within the healthcare environment, specifically in high risk units. The efficacy of a keyboard cover compounded with the antimicrobial polymer was tested by inoculating its surface with each of four organisms commonly encountered in healthcare environments: methicillin-resistant Staphylococcus aureus (MRSA), vancomycin-resistant Enterococcus faecalis (VREF), E. coli, and P. aeruginosa. Recovery of viable bacteria at various time intervals after the initial inoculation revealed bacterial reduction per each organism over time.








Figure 3: 92.1% reduction of viable P. aeruginosa on Biosafe material at T= 240 min.



THE

SPL

Suite 209

1401 Forbes Ave

T-(412) 281-5335

Pittsburgh, PA 15219

Conclusions

The polyurethane material compounded with Biosafe HM 4100 demonstrated efficacy in reducing viability for all four test organisms. P. aeruginosa may be more resistant to the bactericidal properties of the antimicrobial polymer.

Discussion and Implications

Contaminated computer keyboards can be a potential source for bacterial transmission between healthcare providers and patients. The rank order of highest to lowest reduction in viability at T= 240 min. was E. coli > MRSA > VREF > Pseudomonas. Computer keyboards compounded with Biosafe HM 4100 could reduce the transmission of pathogens due to hand carriage during contact with contaminated computer keyboards.

References

Bures S, Fishbain JT, Uyehara CF, Parker JM, Berg BW. Computer ke nosocomial pathogens in the intensive care unit. A 2. Man GS, Olapoju M, Chadwick MV, et al. Bacterial cor 2002;52:31-48.
3. Neely AN, Maley MP, Varden GD. Computer keyboard Infect Dis 1999;29:1358-80.
4. Durbin MV, Maley MP, Varden GD. Computer keyboard Infect Dis 1999;29:1358-80. / NN, Maley MP, warden Sco. computer wyokalisis and effect Dis 1999;29:1358-60. Ia WA, White MS, Gergen MF, Wever DJ. Bacterial contamina Mathematical Control Moon Englemial 2006;27(4):372-7.




Figure 1: 97.8 % reduction of viable MRSA on Biosafe material at T= 240 min

Figure 4: 99.999% reduction of viable E. coli on Biosafe material at T= 240 min. PU Control Biosafe HM

HM 4100

Figure 2: 95% reduction of viable VREF on Biosafe material at T= 240 min. PU Control P. aeruginosa